


### Graph



### Test Data

Test File Name	Rotation Speed [rpm]	Normal Load [N]	Track Radius [mm]	Stage Temp [ ]	Friction Force [N]	Friction Coefficient	Wear Loss [mm]
Bronze PAD-1.csv	300.0	30.0	11.50	30.0	5.04	0.5184	-0.0237
Bronze PAD-2.csv	300.0	30.0	11.50	30.0	5.23	0.5382	0.0381
Bronze PAD-3.csv	300.0	30.0	11.50	30.0	4.87	0.5014	0.0292

### Test Information

1. Operator : John
2. Specimen : Bronze PAD-5
3. Test Standard : Pin-on-Disc Test
4. Room Temperature : 21C
5. Room Humidity : N/A